



W963 PLYSAFE®

EPR High Voltage Tape

Technical Data Sheet

October 2017

Description and Features

W963 Plysafe® is a 30 mil (0,76mm) ethylene propylene rubber, self-amalgamating high voltage tape for insulating and jacketing splices though 69kV. **W963 Plysafe®** amalgamates quickly, yielding a void-free, electrically stable build-up and is ideal for waterproofing. Meets ASTM D-4388, HH-I-553C/Grade A, MIL-I3825B standards.

- Self amalgamating
- Outstanding corona and ozone resistance
- UV resistance
- Excellent moisture, corrosion and chemical resistance

Materials	Backing	Adhesive	Color	Standard Sizes	
	EPR Rubber		Black	Width	Length
				19 mm x 9,1 m (0,75" x 30')	38 mm x 9,1 m (1,5" x 30')
				Other sizes available upon request	
Technical Properties	Characteristic		Typical Value	Test Method	
	Thickness, (mm)		0,76	ASTM D 4325	
	Breaking strength (MPa)		2,3	ASTM D 412	
	Elongation at break (%)		950	ASTM D 412	
	Fusion (2,0mm max)		No Flag	ASTM D 4325	
	Heat Resistance (°C)		130	ASTM D 4325	
	Operating Temp.(°C)				
	Continuous (°C)		90	ASTM D 4325	
	Emergency Overload (°C)		130	ASTM D 4325	
	Water Absorption (%)		0,06	ASTM D 570	
	Ozone Resistance		Pass	ASTM D 4325	
	UV Resistance		Pass	ASTM D 4325	
	Dielectric Strength (kV/mm)		39,5	ASTM D 149	
	Dissipation Factor				
	24h @ 23°C		0,005	ASTM D 150	
	168h @ 70°C		0,015	ASTM D 150	
	Dielectric Constant				
	24h @ 23°C		2,7	ASTM D 150	
	168h @ 70°C		2,9	ASTM D 150	
	Volume Resistivity (Ω.cm)				
	96h @ 23°C and 50% RH		1x10 ¹⁶	ASTM D 257	
	96h @ 23°C and 96% RH		1x 10 ¹³	ASTM D 257	
Recommended Uses	For insulating and jacketing of splices on power cable from 600 volts through 69,000 volts and for building stress cones and for jacketing of terminations on power cable through 35000 volts. Provides a moisture seal for all waterproofing needs and insulations and protects bus components. Due to its highly stable mechanical and chemical properties, W963 Plysafe® is ideal for cable jacket repair and restoration.				
Storage	In original packaging, placed in horizontal position under cover and temperature between 5°C and 35 °C.				
Shelf Life	60 months from date of manufacture.				

Information provided is for reference only. Data in table represent average test results and are not to be used for specification purposes. The product user should make his/her own tests to determine the product's suitability for the intended use

LIMITED WARRANTY: Plymouth warrants that its Product will substantially conform to that products written specifications for a period of one (1) year from the date of shipment, (Unless provided otherwise). Plymouth makes no warranty to the distributor, its customers, or the product's end user for the products merchantability and/or suitability for his/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proved to be defective within the terms described above, and provided buyer shall have first complied with all return policies of Plymouth, PLYMOUTH'S SOLE OBLIGATION AND BUYER'S EXCLUSIVE REMEDY UNDER THIS PRODUCT WARRANTY SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT AS IS PROVED TO BE DEFECTIVE WITHIN THE TIME PERIOD SPECIFIED ABOVE. EXCEPT AS EXPRESSLY SET FORTH HEREIN, PLYMOUTH MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED. In no event shall Plymouth be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products. (rev. 1/2017-2019)